

Technocraft Industries (India) Ltd.

Titeseal Closure Product Data Sheet Stainless Drum Closure With Various Gaskets

General Information

- Manufactured in compliance with ISO-15750-3
- Threads comply with ISO-228
- Raw Material: 316L Stainless Steel
- Finish : Natural Stainless Steel
- To obtain data on insertion process into drum head, our existing customers may <u>click here</u> to obtain insertion process bulletin and insertion gauge drawing specific to this flange insertion gauges are given free to our customers.

Closure is available with any of following standard Technocraft gaskets. Special formulations available

ON request. (To know about chemical compatibility for special products click here or send email or contact postally.)

- Black Nitrile Gasket: Black Nitrile Rubber (NBR) is resistant to petroleum Oils, Aromatic Hydrocarbons, Mineral Oils, Vegetable Oils and many Acids. Black Nitrile has excellent sealing properties.
- White EPDM Gasket: EPDM is a multi-purpose sealing material with good and excellent chemical properties. EPDM is FDA compliant. As plug gasket, it is not recommended for application involving petroleum derivatives.
- Square PE Gasket (For Plug): Square PE gasket due to nature of the Polythelene (PE) have limited heat resistance.
- Round PE Gasket (For Plug): Square PE gasket due to nature of the Polythelene (PE) have limited heat resistance.
- Square Poly Irradiated gasket (For Plug): Improved heat resistance and improved chemical resistance due to cross-linking by electron beam radiation.
- Round Poly Irradiated gasket(For Plug): Improved heat resistance and improved chemical resistance due to cross-linking by electron beam radiation.
- Viton Gasket: Viton is a fluo-elastomer that resists a variety of corrosive fluids at elevated temperature while retaining its mechanical properties.
- Teflon Gasket (For Plug): Although Teflon has excellent chemical resistance.
 However, its sealing capability is very poor! As such Teflon is not suitable as flange
 gasket. Due to its poor sealinh properties Teflon is not recommended as plug gasket.
 Testing under field conditions will be required to determine the appropriate closing
 torque.

Item Code

50mm Flange with

Black Buna - 2TFBSS EPDM - 2TFESS Viton - 2TFVSS Neoprene - 2TFNSS

20mm Flange with

Black Buna - 3TFBSS
EPDM - 3TFESS
Viton - 3TFVSS
Neoprene - 3TFNSS

50mm Plug with

Black Buna - 2TPBSS
EPDM - 2TPESS
Round PE - 2TPRPSS
Square PE - 2TPSPSS

Round Poly Irradiated – 2TPRISS Square Poly Irradiated – 2TPISS

Teflon – 2TPTSS
Viton – 2TPVSS
Neoprene – 2TPNSS

20mm Plug with

Black Buna - 3TPBSS
EPDM - 3TPESS
Round PE - 3TPRPSS
Square PE - 3TPSPSS


Round Poly Irradiated – 3TPRISS Square Poly Irradiated – 3TPISS

Teflon - 3TPTSS Viton - 3TPVSS Neoprene - 3TPNSS



Torque and Temperature Information

Gasket	Temp. (Max)	Oven Time (Max)	20mm (3/4") #	50mm (2") #
Black Nitrile (Black Buna) for Flange & Bung	220° C	15 mins.	8 – 15 ft.lbs 11 – 20 Nm	15 – 25 ft.lbs 20 – 34 Nm
White Buna for Flange & Bung	180° C	20 mins.	8 – 15 ft.lbs 11 – 20 Nm	15 – 25 ft.lbs 20 – 34 Nm
White EPDM for Flange & Bung	205° C	20 mins.	8 – 15 ft.lbs 11 – 20 Nm	15 – 25 ft.lbs 20 – 34 Nm
Black EPDM for Flange & Bung	180° C	20 mins.	8 – 15 ft.lbs 11 – 20 Nm	15 – 25 ft.lbs 20 – 34 Nm
Polyethylene Round Cross Section Square Cross Section for Bung	N.A	N.A	8 – 15 ft.lbs 11 – 20 Nm	15 – 25 ft.lbs 20 – 34 Nm
Irradiated Polyethylene Square Cross Section for Bung	250° C	20 mins.	8 – 15 ft.lbs 11 – 20 Nm	18 – 25 ft.lbs 24 – 34 Nm
Viton for Flange & Bung	230° C	15 mins.	8 – 15 ft.lbs 11 – 20 Nm	15 – 25 ft.lbs 20 – 34 Nm
Teflon for Flange & Bung	107° C	15 mins.	10 – 15 ft.lbs 14 – 20 Nm	18 – 25 ft.lbs 24 – 34 Nm



2"(ISO-228)


Minimum values are meant for Drum Maker and Maximum for Drum Filler

Standard Packing

Item	Box	Box Size (mm)
	Quantity	
50mm	100	300(L) x 300(W) x 150(H)
Flange		
20mm	100	180 x 180 x 85
Flange		
50mm	100	210 x 180 x 190
Plug		
20mm	100	125 x 125 x 85
Plug		

- Boxes are marked with item code.
- Pallets are stretch wrapped.
- Optional Special packaging as per customer's requirement.





More information can be availed by <u>clicking here</u> or by contacting our head quarters as per details on our web page.